

Product Specifications

Product: Savoir Faire
 Date: November 2005
 Description: Fine gauge, High density Luxury Plush Pile
 Pile Fibre: 100% Pure New selected carpet wools
 Fibre Quality: Woollen spun, multi-ply, twisted and chem set
 Gauge: 3.175 mm (1/8")
 Stitch Rate: 38.8 per 100mm
 Pile Mass: 1627 gm/m² (48 oz/yd²)
 Pile Height: 10 mm
 Colouration: Stock Dyed
 Primary Backing: 112 g/m² (3.3 oz/yd²) woven polypropylene
 Secondary Backing: 237 g/m² (7 oz/yd²) woven jute
 Laminate: 610 g/m² (18 oz/yd²) synthetic latex
 Total Weight: 9.4 kg/LM (76.3 oz/yd²)
 Width: 3.66 metres

A.C.C.S. Reg. No.: 94120
 A.C.C.S. Grade: Residential Extra Heavy Duty 1 (Stairs) - 5 Star
 Contract Medium Duty (Stairs) - 2 Star
 Critical Radiant Flux: CHF Mean Result kw/m² (Direct Stick)
 (Burning Behaviour) Smoke Value % min (Direct Stick)
 AS/ISO 9239-1:2003 Passes requirements of BCA spec C1.10a
 Part 1 - Test Class 9a; 9b; 9c Buildings (Direct Stick)
 Product Features:

- 12 Sophisticated designer colours combining the natural beauty and luxury of Pure New Wool.
- Increased thermal and acoustic comfort.
- Superior durability and appearance.
- The use of chair pads is mandatory.
- Must be laid in accordance with AS 2455.1995.
- Subject to Tuftmaster's 'Terms of Trading.'

BEAUVAIS

Product Specifications

Product: Beauvais 40oz
 Date: November 2005
 Description: Fine gauge, high density Luxury Plush Pile
 Pile Fibre: 100% Pure New selected carpet wools
 Fibre Quality: Woollen spun, multi-ply, twisted & chem set
 Gauge: 3.175 mm (1/8")
 Stitch Rate: 34.3 per 100mm
 Pile Mass: 1356 gm/m² (40 oz/yd²)
 Pile Height: 7.5 mm
 Colouration: Stock Dyed
 Primary Backing: 112 g/m² (3.3 oz/yd²) woven polypropylene
 Secondary Backing: 237 g/m² (7 oz/yd²) woven hessian
 Laminate: 610 g/m² (18 oz/yd²) synthetic latex
 Total Weight: 8.5 kg/LM (68.3 oz/yd²)
 Width: 3.66 metres

A.C.C.S. Reg. No.: 94121
 A.C.C.S. Grade: Residential Extra Heavy Duty 2 (Stairs) - 6 Star
 Contract Heavy Duty (Stairs) - 3 Star
 Critical Radiant Flux: CHF Mean Result kw/m² (Conventional)
 (Burning Behaviour) Smoke Value % min (Conventional)
 AS/ISO 9239-1:2003 Passes requirements of BCA spec C1.10a
 Part 1 - Test Class 9a; 9b; 9c Buildings (Conventional)
 Product Features:

- 12 Sophisticated designer colours combining the natural beauty and luxury of Pure New Wool.
- Increased thermal and acoustic comfort.
- Superior durability and appearance.
- The use of chair pads is mandatory.
- Must be laid in accordance with AS 2455.1995.
- Subject to Tuftmaster's 'Terms of Trading.'

- Shading:** All cut velvet carpets are subjected to shading, pile pressure, highlighting, permanent pile reversal or crushing. This is not a manufacturing fault. It is a natural characteristic of all cut pile carpets. For further information please contact the Carpet Institute Of Australia.
- Installation:** All carpet installations are to be in accordance with AS2455.1:1995 unless otherwise stated in writing by Tuftmaster Carpets.
 Carpet is a textile that is subjected to extreme variations in temperature and tension in the manufacturing process. During this process variances may occur in both the width and length of this patterned carpet and as a result an exact pattern match cannot be guaranteed. A reasonable pattern match may be obtained when installing carpet conventionally over an underlay and when installed by trained, experienced and professional carpet layers. Pattern matching cannot be guaranteed when installed by the direct stick or dual bond method as this only allows for minor stretching and adjustments of the pattern during installation.
 When installing patterned carpets on open floors it is a requirement that the carpet layers have unrestricted access to the entire floor being laid. The initial run of carpet on any type of installation is the most critical and ensures that the project is set out accurately prior to joining, to ensure the best possible pattern match over the entire floor area is achieved. No acceptable pattern match can be guaranteed if the carpet layers are only provided part floors at a time.
- Carpet Joins:** Tuftmaster Carpets specify that when laying conventionally or dual bond that all cut edges to be joined must be tipped with an edge sealing latex adhesive (minimum 60% component) and be given sufficient time to cure properly prior to heat taping (time is dependant on site conditions and temperature). It is the installers responsibility to ensure that the correct heat tapes are used when installing carpet by both methods.
- Dye Variation:** Shade or pattern variations may occur from sample and between dye lots and within production runs due to the many variances in the manufacturing of carpet, however these variations will be within recognized textile industry standards.
- Cleaning:** Carpet should be cleaned and maintained in accordance with AS 3733:1995. 1.



HEAD OFFICE
TUFTMASTER CARPETS
PTY. LTD.

A.C.N. 004 802 564

Cope Street, Preston, Victoria 3072.
 Telephone: 61 3 9791 1388
 Facsimile: 61 3 8480 4080
 Email: email@tuftmaster.com.au

Interstate Offices

N.S.W.
 (02) 9555 2177
Queensland
 0402 119 538
 1800 062 076
S.A.
 0402 119 541

W.A.
 0402 119 545
Tasmanian Agent
 (03) 6234 9855

