

## Product Specification

### **Vivant 48**

<b>Date:</b>	March 2005		
<b>Description:</b>	Fine gauge, low profile, high density patterned level loop.		
<b>Pile Fibre:</b>	100% selected carpet wools.		
<b>Fibre Quality:</b>	Semi worsted, multi-ply, twisted and non-heat set.		
<b>Gauge:</b>	2.54 mm (1/10").		
<b>Stitch Rate:</b>	48.0 per 100 mm.		
<b>Pile Weight:</b>	1627 g/m <sup>2</sup> (48 oz/yd <sup>2</sup> ).		
<b>Pile Height:</b>	5.0 mm.		
<b>Colouration:</b>	Stock dyed.		
<b>Primary Backing:</b>	112 g/m <sup>2</sup> (3.3 oz/yd <sup>2</sup> ) heat stabilised woven polypropylene.		
<b>Secondary Backing:</b>	237 g/m <sup>2</sup> (7 oz/yd <sup>2</sup> ) woven jute.		
<b>Laminate:</b>	1011 g/m <sup>2</sup> (29.8oz/yd <sup>2</sup> ) synthetic latex.		
<b>Total Weight:</b>	10.9 kg / LM (88.0 oz/yd <sup>2</sup> ).		
<b>Width:</b>	3.66 metres.		
<b>A.C.C.S Reg No:</b>	23148		
<b>A.C.C.S. Grade:</b>	Residential Extra Heavy 2, Stairs – 6 ★ Contract Extra Heavy Duty, Stairs – 4 ★		
<b>Moth Proofed:</b>	In accordance with AS2001.6.1.		
<b>AS:1530:3</b>	Ignitability	16	Range 0-20
	Spread of Flame	0	Range 0-10
	Heat Evolved	0	Range 0-10
	Smoke Developed	3	Range 0-10
<b>BS 1006.B02:</b>	Colourfastness to light	5	
<b>AS 2111.19.2:</b>	Colourfastness to shampoo	3-4	
<b>AS 2111.19.1:</b>	Colourfastness to rubbing	3-4	
<b>AS 2001.4.16:</b>	Colourfastness to solvents	3-4	
<b>Product Features:</b>	*7 sophisticated natural contemporary colourations. *Increased thermal and acoustic comfort. *Superior appearance retention when correctly maintained.		
<b>Notes:</b>	*Seam Sealer to be used on all seams. *The use of chair pads is mandatory. *Must be laid in accordance with AS 2455. *Subject to Tuftmaster's 'Terms of Trading'.		
<b>Colour Range:</b>	Arabian Brown 150	Armada 600	Brazil 190
	Maduro 140	Solitaire 500	Vespertine 900
	Zephyr 100		

**Please contact your Tuftmaster Representative for further information**